

SC 00001

## **BASE SHABBY**

## **Technical Sheet**

NAME: BASE SHABBY

**GROUP:** washable water-based paint

<u>USE</u> modified acrylic washable water-based paint for interiors and exteriors,

breathable, water-repellent, with good covering power.

**FEATURES:** specific weight: White 1425 + 30 g/L at 25°C

**coverage:**  $9 - 11 \text{ m}^2/\text{L}$  for two coats applied with a brush on

a smooth surface

binder: modified acrylic dispersion

aesthetic effect: matte

**colours:** white and all colours in the Valclone catalogue

packaging: L 1 - L 2.5

brilliance: UNI EN ISO 2813 Matte – 15 Gloss Unit resistance to washing: UNI 10560 over 5000 abrasive cycles resistance to abrasion: DIN 53778 over 5000 abrasive cycles

**covering capacity:** UNI EN 13300 Class 3 – 97.5

Volatile Organic Class: A/c; VOC: 15 g/L (maximum); Phase II

Compounds (VOC) limit (from 1.1.2010) 40 g/L

emission limit, according to directive

2004/42/EC

**DRYING:** on the surface: 30 minutes at 20°C

recoating: 4 hours at 20°C in depth: 12 hours at 20°C

PREPARATION OF THE

**SURFACE AND** 

**APPLICATION CYCLE:** 

Assess the state of the surface and remove any traces of old paint or dust. Apply one coat of Fissativo and after 6 hours at 20° C level out any small

holes, cracks and cracking with Stucco. To ensure even absorption, apply again diluted Fissativo only on the plastering and after 6-8 hours apply Base Shabby. Wait at least 4 hours at 20°C between the first and the

20% with tap water

second coat of Base Shabby.

PREPARATION OF THE

**PRODUCT:** 

**APPLICATION:** system: brush - roller - sprayer

coats: 2 to cover

**COMMENTS:.** 

The storage and application temperature must be between + 5°C and +35°C.

dilution:

Clean all tools with water immediately after use.

Do not dispose of the paint residues and washing water in rivers or in the sewer system

**Technical Sheet n° SC 00001 issued by the Quality Control Department:** 

Edition n° 1 June 2018